DIAMOND ADHESIVE



Advantages

- · High polymer modified adhesive
- · Easy mixing & smooth application & better workability
- · For use on walls & floors in interior & exterior.
- · High strength & Water resistance
- · DIAMOND ADHESIVE meets the performance requirements of IS 15477: 2004
- "Specification for Adhesives for use with Wall Tiles, Floor Tiles, Marbles, Granites and Stones"

Application Areas

Walls ,Floors ,Interiors ,Exteriors ,Dry & Wet areas Showers , Swimming Pools

Method of Application

1 Surface Preparation

- * The surface should be sound, clean, and free from dirt, oil or grease before PROOFER DIAMOND ADHESIVE is applied.
- * Substrate should be in Saturated Surface Dry (SSD) condition before application of adhesive. Substrates should be in plumb before application of adhesive

2 Mixing

- * Mix 20 kg of PROOFER DIAMOND ADHESIVE with 5 to 6 liters of water.
- * Mix to a uniform lump-free consistency using a forced action mixer.
- * Keep it for approximately 5 minutes to fatten it.
- * Hand mixing is recommended for small quantities only.
- * Mix as much quantity as can be consumed in 45 min.

3 Application

Apply PROOFER DIAMOND ADHESIVE paste on substrate with plain side of notch trowel. Press paste firmly to work into substrate.

- * Comb with notch trowel with notched side, notch trowel to be selected as per required bed thickness.
- * Spread as much adhesive paste as can be tiled within 15 minutes.
- * Start placing/fixing of tiles & tap using beating block or rubber mallet.
- * For large format tiles & stone provide back butter for 100 % coverage & firm bonding.
- * Periodically remove a tile to check transfer of material on tile. Also check spread of adhesive, if not proper and if becomes non-sticky then scrap it & apply paste again.

4 Grouting

* Grouting should preferably be carried out at least 24 hours after the completion of tiling.

5 CLEANING

* Clean the tools & equipments with potable water immediately after use.



Technical Information

PROPERTIES RESULTS

Appearance Free flowing powder

Pot life @ 25OC, minutes 35 to 45

Open time, minutes 25

Adjustability time, minutes 5

Trafficable time, Hrs 24

Shear adhesion, KN 8-10

Tensile adhesion strength,

14 days, N/mm2 2758 kN force

Precautions & Limitations

* Always add powder to liquid and not liquid to powder.

* While working in temperature more than 35OC (95OF) always dampen the substrate & finish faster.

* Tiling should not be done when surface temperature is below 4OC.

Health & Safety Precautions

Protective clothing, such as gloves and goggles, should be worn.

- * Treat any contact to the skin or eyes with fresh water immediately.
- * Do not induce vomiting & seek medical
- * Assistance immediately.
- * Reseal pack after use and ensure product is stored as instructed...

Pack Size

20 kg

Coverage

approximately 4.5 to 5 m²/20kg @ 3 mm thickness when using a thin trowel